

**IN THE CLAIMS:**

The text of all pending claims, (including withdrawn claims) is set forth below. Cancelled and not entered claims are indicated with claim number and status only. The claims as listed below show added text with underlining and deleted text with ~~striketrough~~. The status of each claim is indicated with one of (original), (currently amended), (cancelled), (withdrawn), (new), (previously presented), or (not entered).

**Please CANCEL claim 6 and AMEND claims 1 and 5 in accordance with the following:**

1. **(currently amended)** A polymer foam comprising a plurality of cells defined by cell walls which constitute a polymer matrix,  
     said polymer matrix being comprised of:  
     5 to 100 parts by weight, relative to 100 parts by weight of the total of components (A) and (B), of (A) a hydrogenated copolymer obtained by hydrogenating an unhydrogenated copolymer ~~comprising vinyl aromatic monomer units and conjugated diene monomer units~~, said unhydrogenated copolymer being a block copolymer containing at least one copolymer block S which is comprised of vinyl aromatic monomer units and conjugated diene monomer units and at least one homopolymer block H of vinyl aromatic monomer units, wherein said at least one copolymer block S ~~which~~ has a vinyl bond content of from 5 % to less than 40 % as measured with respect to conjugated diene monomer units, wherein said unhydrogenated copolymer is at least one polymer selected from the group consisting of copolymers which are, respectively, represented by the following formulae (2) to (6) and (8) to (10):

(2) S-H,

(3) S-H-S,

(4) (S-H)<sub>m</sub>-X,

(5) (S-H)<sub>n</sub>-X-(H)<sub>p</sub>,

(6) H-S-H,

(8) H-S-E,

(9) E-S-H-S and

(10) (E-S-H)<sub>m</sub>-X

wherein each S independently represents a copolymer block comprised of vinyl aromatic monomer units and conjugated diene monomer units, each H independently represents a homopolymer block of vinyl aromatic monomer units, each E independently represents a homopolymer block of conjugated diene monomer units, each X independently represents a residue of a coupling agent, each m independently represents an integer of 2 or more, and each of n and p independently represents an integer of 1 or more, and

95 to 0 part by weight, relative to 100 parts by weight of the total of components (A) and (B), of (B) at least one polymer selected from the group consisting of an olefin polymer other than said hydrogenated copolymer (A) and a rubbery polymer other than said hydrogenated copolymer (A),

said hydrogenated copolymer (A) having the following characteristics (1) and (2):

(1) said hydrogenated copolymer (A) has a content of said vinyl aromatic monomer units of from more than 40 % by weight to 60 % by weight, based on the weight of said hydrogenated copolymer (A), and

(2) at least one peak of loss tangent ( $\tan\delta$ ) is observed at -40 °C to lower than -10 °C in a dynamic viscoelastic spectrum obtained with respect to said hydrogenated copolymer (A),

said polymer foam having a specific gravity of from 0.05 to 0.5.

2. **(original)** The polymer foam according to claim 1, wherein the amounts of said hydrogenated copolymer (A) and said polymer (B) are, respectively, 5 to 95 parts by weight and 95 to 5 parts by weight, relative to 100 parts by weight of the total of components (A) and (B).

3. **(original)** The polymer foam according to claim 1 or 2, wherein substantially no crystallization peak ascribed to at least one hydrogenated copolymer block obtained by hydrogenating said at least one copolymer block S is observed at -50 to 100 °C in a differential scanning calorimetry (DSC) chart obtained with respect to said hydrogenated copolymer (A).

4. **(previously presented)** The polymer foam according to claim 1 or 2, wherein at least one of said at least one copolymer block S in said unhydrogenated copolymer has a structure wherein said vinyl aromatic monomer units are distributed in a tapered configuration.

5. **(currently amended)** The polymer foam according to claim 1 or 2, wherein ~~said unhydrogenated copolymer further contains a homopolymer block H of vinyl aromatic monomer~~

~~units~~, the amount of said at least one homopolymer block H of vinyl aromatic monomer units in said unhydrogenated copolymer ~~is being~~ in the range of from 1 to 40 % by weight, based on the weight of said unhydrogenated copolymer.

6. **(canceled)**

7. **(previously presented)** The polymer foam according to claim 1 or 2, wherein said hydrogenated copolymer (A) has bonded thereto a modifier having a functional group.

8. **(original)** The polymer foam according to claim 7, wherein said modifier is a first-order modifier having at least one functional group selected from the group consisting of a hydroxyl group, an epoxy group, an amino group, a silanol group and an alkoxysilane group.

9. **(withdrawn)** The polymer foam according to claim 7, wherein said modifier comprises a first-order modifier and, bonded thereto, a second-order modifier,

wherein said first-order modifier has at least one functional group selected from the group consisting of a hydroxyl group, an epoxy group, an amino group, a silanol group and an alkoxysilane group, and

wherein said second-order modifier has at least one functional group selected from the group consisting of a hydroxyl group, a carboxyl group, an acid anhydride group, an isocyanate group, an epoxy group and an alkoxysilane group.

10. **(withdrawn)** The polymer foam according to claim 1 or 2, wherein said olefin polymer as component (B) is at least one ethylene polymer selected from the group consisting of a polyethylene, an ethylene/propylene copolymer, an ethylene/propylene/butylene copolymer, an ethylene/butylene copolymer, an ethylene/hexene copolymer, an ethylene/octene copolymer, an ethylene/vinyl acetate copolymer, an ethylene/acrylic ester copolymer and an ethylene/methacrylic ester copolymer.

11. **(previously presented)** The polymer foam according to claim 1 or 2, wherein said rubbery polymer as component (B) is at least one member selected from the group consisting of a 1,2-polybutadiene, a hydrogenation product of a conjugated diene homopolymer, a copolymer comprised of vinyl aromatic monomer units and conjugated diene monomer units and a hydrogenation product thereof, a block copolymer comprised of a homopolymer block of vinyl

aromatic monomer units and at least one polymer block selected from the group consisting of a homopolymer block of conjugated diene monomer units and a copolymer block comprised of vinyl aromatic monomer units and conjugated diene monomer units and a hydrogenation product thereof, an acrylonitrile/butadiene rubber and a hydrogenation product thereof, an ethylene/propylene/diene rubber (EPDM), a butyl rubber and a natural rubber.

12. **(original)** The polymer foam according to claim 11, wherein said rubbery polymer as component (B) is at least one member selected from the group consisting of a hydrogenation product of a copolymer comprised of vinyl aromatic monomer units and conjugated diene monomer units, said hydrogenation product having a vinyl aromatic monomer unit content of from more than 60 % by weight to 90 % by weight, based on the weight of said hydrogenation product; and a block copolymer comprised of a homopolymer block of vinyl aromatic monomer units and at least one polymer block selected from the group consisting of a homopolymer block of conjugated diene monomer units and a copolymer block comprised of vinyl aromatic monomer units and conjugated diene monomer units and a hydrogenation product thereof.

13. **(previously presented)** The polymer foam according to claim 1 or 2, which exhibits an impact resilience of 40 % or less.

14. **(previously presented)** The polymer foam according to claim 1 or 2, which has a specific gravity of from 0.1 to 0.3.

15. **(previously presented)** The polymer foam according to claim 1 or 2, which is a shock absorber.

16. **(canceled)**

**THE REMAINDER OF THIS PAGE INTENTIONALLY LEFT BLANK**